


**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 40.1mm
- Effective Area ( $A_e$ ): 45.5mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 40.9mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 1825mm<sup>3</sup>

**Approximate Weight (without Gap): 9.4g/Set**



## EE1910A Un-gapped

**Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)	$P_v$ (W/set)	Ordering code
CF295	3000 ± 20%	2700 +30%/-20%	<0.22 (100mT,100kHz,100°C)	CF295 EE1910A

## Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	19.1	19.5	18.7
B	-	-	14.0
C	8.0	8.18	7.82
D	-	-	5.7
E	4.75	4.95	4.55
F	9.5	9.7	9.3

