

**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.  
**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 44.9mm
  - Effective Area ( $A_e$ ): 65.22mm<sup>2</sup>
  - Effective Area ( $A_{Min}$ ): 61.9mm<sup>2</sup>
  - Effective Volume ( $V_e$ ): 2928mm<sup>3</sup>
- Approximate Weight (without Gap): 14.5g/Set**



## EE2011S Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)	$P_v$ (W/set)	Ordering code
CF295	3000 ± 20%	3500 +30%/-20%	≤0.35 (100mT,100kHz, 100°C)	CF295 EE2011S

## Dimensions

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	20.4	20.4	19.6
B	14.1	14.9	14.1
C	10.1	10.1	9.7
D	7.20	7.4	7.0
E	5.9	5.9	5.5
F	10.65	10.8	10.5

