


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 73.5mm
- Effective Area (A_e): 42.1mm²
- Effective Area (A_{Min}): 41.5mm²
- Effective Volume (V_e): 3094mm³

Approximate Weight: 15.8g/Set



EE2532 Un-gapped

Test Conditions: 1KHz/100mV/N=100/25°C

Material	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_V (W/set)	Ordering code
CF295	3000 \pm 20%	1550 +30%/-20%	<0.37 (100mT, 100kHz, 100°C)	CF295 EE2532

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	25.3	25.8	25.0
B	19.3	19.7	19.1
C	15.9	16.1	15.7
D	12.7	13.0	12.4
E	6.5	6.8	5.25
F	7.0	7.0	6.5

