


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 80.7mm
- Effective Area (A_e): 100.0mm²
- Effective Area (A_{Min}): 100.0mm²
- Effective Volume (V_e): 8070mm³

Approximate Weight (without Gap): 36.0g/Set



EE3510 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 ± 20%	3300 +30%/-20%	≤0.96 (100mT,100kHz,100°C)	CF295 EE3510

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	35.0	35.5	34.5
B	25.0	25.5	24.5
C	17.5	17.75	17.25
D	12.5	12.75	12.25
E	10.0	10.3	9.7
F	10.0	10.3	9.7

