


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.
Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 97.0mm
 - Effective Area (A_e): 240.0mm²
 - Effective Area (A_{Min}): 229.0mm²
 - Effective Volume (V_e): 23300mm³
- Approximate Weight: 112.25gm/set**



EE4220 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 ± 20%	6500 +30%/-20%	≤2.80 (100mT,100kHz,100°C)	CF295 EE4220

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	42.0	43.0	41.3
B	29.5	30.7	29.5
C	21.2	21.2	20.8
D	14.8	15.5	14.8
E	12.2	12.2	11.7
F	20.0	20.0	19.2

