


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 89.6mm
- Effective Area (A_e): 236.8mm²
- Effective Area (A_{Min}): 233.0mm²
- Effective Volume (V_e): 21169mm³

Approximate Weight (without Gap): 103.0gm/Set



EE4716 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_V (W/set)	Ordering code
CF295	3000 \pm 20%	7200 +30%/-20%	≤ 2.54 (100mT,100kHz,100°C)	CF295 EE4716

Dimensions

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	47.15	47.65	46.65
B	31.6	-	31.6
C	19.7	19.83	19.57
D	-	-	12.1
E	15.65	15.85	15.45
F	15.65	15.85	15.45

