


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 204.0mm
 - Effective Area (A_e): 386.0mm²
 - Effective Area (A_{Min}): 371.8mm²
 - Effective Volume (V_e): 78744mm³
- Approximate Weight (without Gap): 394g/Set**



EE7091 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	5300 +30%/-20%	\leq 9.45 (100mT,100kHz, 100°C)	CF295 EE7091

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	70.0	71.5	68.5
B	-	-	48.5
C	45.5	46.0	45.0
D	35.5	36.0	35.0
E	19.5	20.0	19.0
F	19.5	20.0	19.0

