


**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 137.0mm
- Effective Area ( $A_e$ ): 367.9mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 361.5mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 50402mm<sup>3</sup>

**Approximate Weight (without Gap): 260g/Set**



## EE7219 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)/Set	$P_v$ (W/set)	Ordering code
CF295	3000 $\pm$ 20%	7300 +30%/-20%	$\leq$ 6.05 (100mT,100kHz,100°C)	CF295 EE7219

## Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	72.4	73.85	70.95
B	53.35	54.45	52.25
C	27.95	28.1	27.8
D	18.05	18.3	17.8
E	19.05	19.43	18.67
F	19.05	19.43	18.67

