

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 55.6mm
 - Effective Area (A_e): 19.3mm²
 - Effective Area (A_{Min}): 18.7mm²
 - Effective Volume (V_e): 1075mm³
- Approximate Weight (without Gap): 5.5g/Set**



EEL1605 Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL- Value(nH)	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	1000 +30%-/20%	≤ 0.13 (100mT,100kHz,100°C)	CF295 EEL1605

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	16.0	16.3	15.7
B	12.1	12.4	11.8
C	12.45	12.65	12.25
D	10.25	10.45	10.05
E	4.0	4.2	3.8
F	4.8	5.0	4.6

