


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 34.9mm
 - Effective Area (A_e): 17.3mm²
 - Effective Area (A_{Min}): 16.7mm²
 - Effective Volume (V_e): 604mm³
- Approximate Weight (without Gap): 3.7g/Set**



EEL1605B Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_V (W/set)	Ordering code
CF295	3000 ± 20%	1150 +30%/-20%	≤0.07 (100mT,100KHz, 100°C)	CF295 EEL1605B

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	16.1	16.7	15.5
B	12.1	12.4	11.8
C	6.95	7.1	6.8
D	5.4	5.6	5.2
E	4.0	4.2	3.8
F	4.8	5.0	4.6

