


**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

**Effective Parameters irrespective of material grade (per set)**

- Effective Length ( $L_e$ ): 71.0mm
  - Effective Area ( $A_e$ ): 76.0mm<sup>2</sup>
  - Effective Area ( $A_{Min}$ ): 71.0mm<sup>2</sup>
  - Effective Volume ( $V_e$ ): 5377mm<sup>3</sup>
- Approximate Weight (without Gap): 27.0g/Set**



## ETD2910 Un-gapped

Test Conditions: 1KHz/100mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)	$P_v$ (W/set)	Ordering code
CF295	3000 $\pm$ 20%	2650 +30%/-20%	<0.64 (100mT,100kHz, 100°C)	CF295 ETD2910

## Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	30.6	30.6	29.0
B	22.0	23.4	22.0
C	16.0	16.0	15.6
D	-	-	10.7
E	9.8	9.8	9.2
F	9.8	9.8	9.2

