

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 78.6mm
- Effective Area (A_e): 97.1mm²
- Effective Area (A_{Min}): 91.6mm²
- Effective Volume (V_e): 7640mm³

Approximate Weight: 39g/Set



ETD3411 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 ± 20%	3100 +30%/-20%	≤0.91 (100mT, 100kHz, 100°C)	CF295 ETD3411

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	34.0	35.0	33.4
B	25.6	27.0	25.6
C	17.5	17.5	17.1
D	-	-	11.8
E	11.1	11.1	10.5
F	11.1	11.1	10.5

