


Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 103mm
- Effective Area (A_e): 173mm²
- Effective Area (A_{Min}): 172mm²
- Effective Volume (V_e): 17819mm³

Approximate Weight (without Gap): 89 gm/Set



ETD4415 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	4300 +30%/-20%	\leq 2.14 (100mT, 100kHz, 100°C)	CF295 ETD4415

Dimension:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	43.8	45.0	43.0
B	32.5	34.1	32.5
C	22.5	22.5	22.1
D	-	-	16.3
E	15.2	15.2	14.4
F	15.2	15.2	14.4

