

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 127.0mm
 - Effective Area (A_e): 280.0mm²
 - Effective Area (A_{Min}): 280.0mm²
 - Effective Volume (V_e): 35500mm³
- Approximate Weight (without Gap): 177g/Set**



ETD5419 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	P_v (W/set)	Ordering code
CF295	3000 \pm 20%	5600 +30%/-20%	<4.26 (100mT,100kHz,100°C)	CF295 ETD5419

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	54.5	55.8	53.2
B	41.2	42.3	40.1
C	27.6	27.8	27.4
D	20.2	20.6	19.8
E	18.9	19.3	18.5
F	18.9	19.3	18.5

