

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.
Effective Parameters irrespective of material grade (per set)

- Effective Length (L_e): 139.0mm
- Effective Area (A_e): 368.0mm²
- Effective Area (A_{Min}): 368.0mm²
- Effective Volume (V_e): 51200mm³

Approximate Weight (without Gap): 262g/Set



ETD5922 Un-gapped

Test Conditions: 1KHz/150mV/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	P_V (W/set)	Ordering code
CF295	3000 ± 20%	6500 +30%/-20%	<6.14 (100mT,100kHz,100°C)	CF295 ETD5922

Dimensions:

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	59.8	60.2	58.4
B	44.7	45.8	43.6
C	31.0	31.2	30.8
D	22.45	22.9	22.0
E	21.65	22.1	21.2
F	21.65	22.1	21.2

