









<b>Application</b>	Broadband Transformers
<b>Material</b>	Mn-Zn

Material Properties	Conditions	Symbol	Value	Unit
<b>Initial Permeability</b>	25°C, 10kHz, $\leq 0.25\text{mT}$	$\mu_i$	7000 $\pm 20\%$	
<b>Flux Density</b>	25°C; 10kHz; 1200A/m	$B_s$	380	mT
	100°C; 10kHz; 1200A/m	$B_s$	240	mT
<b>Coercive Field Strength</b>	25°C; 10kHz	$H_c$	9	A/m
	100°C; 10kHz	$H_c$	8	A/m
<b>Hysteresis Material Constant</b>	25°C;	$\eta_B$	$< 1.1$	$10^{-6}\text{mT}$
<b>Curie Temperature</b>	10kHz; $\leq 0.25\text{mT}$	$T_c$	$> 130$	°C
<b>Density</b>	25°C	$\rho$	$4.8 \times 10^3$	kg/m <sup>3</sup>
<b>Resistivity</b>	25°C	$\rho_{DC}$	0.2	$\Omega\text{m}$
<b>Relative Core Loss Factor</b>	25°C; 10 kHz	$\tan \delta/\mu_i$	$\leq 2$	$*10^{-6}$
	25°C; 300 kHz	$\tan \delta/\mu_i$	$\leq 60$	$*10^{-6}$





**Prodin Ferrite S.L.**

Calle A, 27, 08620 Sant Vicenç dels Horts, Barcelona (Spain)

Tel.: +34 93 672 46 10

[info@prodinferrite.com](mailto:info@prodinferrite.com) [www.prodinferrite.com](http://www.prodinferrite.com)