




**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc; as per IEC standards

**Effective parameters irrespective of material grade (per set)**


Parameter	Value	Unit
Effective Length ( $L_e$ )	38.0	mm
Effective Area ( $A_e$ )	25.0	mm <sup>2</sup>
Effective Area ( $A_{Min}$ )	24.5	mm <sup>2</sup>
Effective Volume ( $V_e$ )	950	mm <sup>3</sup>
Approx. Weight (without gap)	4.8	g/set



**EE1905 Un-gapped (OL)**

**Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)/Set	$P_v$ (W/set)	Ordering code
CF292	1800 ±20%	1100 +30%/-20%	≤0.12 (100mT,100kHz,100°C)	CF292 EE1905 OL
CF139	2100 ±20%	1250 +30%/-20%	≤0.095 (100mT,100kHz,100°C)	CF139 EE1905 OL
CF297	2300 ±20%	1350 +30%/-20%	≤0.085 (100mT,100kHz,100°C)	CF297 EE1905 OL
CF124	2500 ±20%	1450 +30%/-20%	≤0.14 (200mT,25kHz,100°C)	CF124 EE1905 OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value



**Prodin Ferrite S.L.**

Calle A, 27, 08620 Sant Vicenç dels Horts, Barcelona (Spain)

Tel.: +34 93 672 46 10

[info@prodinferrite.com](mailto:info@prodinferrite.com) [www.prodinferrite.com](http://www.prodinferrite.com)